

PRODUCT DESCRIPTION

Stonchem 658HD is a solvent-free, high-performance epoxy, heavy-duty lining system applied at a nominal thickness of 3.81 mm. A fiberglass scrim cloth is embedded into the basecoat broadcast liquids to reinforce the system and mitigate stress concentrations which prevent cracking. The heavily broadcast topcoat over the fiberglass scrim cloth helps protect the fabric by providing a wear layer that adds durability and abrasion resistance to the system – more than a typical reinforced lining system. Stonchem 658HD has excellent resistance to acids, alkalis and solvents.

USES, APPLICATIONS

- Process slabs
- Tank farms
- Chemical loading and unloading areas
- Spill containment areas
- Truck unloading areas

PRODUCT ADVANTAGES

- Excellent resistance to chemical attack
- Excellent abrasion and impact resistance
- Exceptional thermal shock resistance
- Superior bonding qualities
- High cohesive strength
- Low permeability
- Low odor

CHEMICAL RESISTANCE

Stonchem 658HD is formulated to resist a variety of chemical solutions. (Refer to the Stonchem 600 Series Chemical Resistance Guide for lists of reagent concentrations and temperature recommendations.)

PACKAGING

Stonchem 658HD is packaged in units for easy handling. Each unit consists of:

Broadcast Liquids/Topcoat

- 8 cartons of liquid, each carton contains:
 - 2 cans of Amine
 - 2 cans of Resin

7 bags of Silica Broadcast Aggregate

4 bags of Aluminum Oxide Aggregate

Fiberglass Scrim Cloth

1 roll @ 22.7 m²

COVERAGE

Each unit of Stonchem 658HD will cover approximately 22.76 m² at a thickness of 3.81 mm.

STORAGE CONDITIONS

Store all components between 10 to 24°C in a dry area. Keep out of direct sunlight. The shelf life is 3 years in the original, unopened container.

SUBSTRATE

Stonchem 658HD, with appropriate primer, is suitable for application over concrete and the following uncoated newly applied Stonhard mortars and grouts: GS, HT, UR, UT, TG6, TG8, CR5 and PM5. For questions regarding other possible substrates or an appropriate primer, contact your local Stonhard representative or Technical Service.

SUBSTRATE PREPARATION

Proper preparation is critical to ensure an adequate bond and system performance. The substrate must be dry and properly

PHYSICAL CHARACTERISTICS

Tensile Strength	58.6 N/mm ² (ASTM D-638)
Flexural Strength	89.6 N/mm ² (ASTM C-580)
Flexural Modulus of Elasticity	5.1 x 10 ³ N/mm ² (ASTM C-580)
Hardness	75 to 85 (ASTM D-2240, Shore D)
Abrasion Resistance	0.056 gm weight loss (ASTM D-4060, CS-17)
Thermal Coefficient of Linear Expansion.....	1.9 x 10 ⁻⁵ mm/m°C (ASTM C-531)
Color	Gray
Cure Rate	12 to 18 hours tack free 70°F/21°C
VOC	Broadcast Liquids/Topcoat 6 g/l (ASTM D-2369, Method E)

Note: The above physical properties were measured in accordance with the referenced standards. Samples of the actual floor system, including binder and filler, were used as test specimens. All sample preparation and testing is conducted in a laboratory environment, values obtained on field-applied materials may vary and certain test methods can only be conducted on lab-made test coupons.

prepared utilizing mechanical methods. Questions regarding substrate preparation should be directed to your local Stonhard representative or Technical Service.

APPLICATION GUIDELINES

For optimal working conditions, substrate temperature must be between 15 to 27°C. Cold areas must be heated until the slab temperature is above 13°C to ensure the material achieves a proper cure. A cold substrate will make the material stiff and difficult to apply. Warm areas or areas in direct sunlight must be shaded or arrangements made to work during evenings or at night. A warm substrate (15 to 27°C) will aid in the material's workability; however, a hot substrate (27 to 37°C) or a substrate directly in the sun will shorten the material's working time and can cause other phenomenon such as pinholing and bubbling. Substrate temperature must be greater than 3°C above dew point during application and curing period.

Application and curing times are dependent upon ambient and surface conditions. Consult Stonhard's Technical Service Department if conditions are not within recommended guidelines.

PRIMING

Vacuum the surface before priming and make sure the substrate is dry. The use of Stonchem Epoxy Primer is necessary in 658HD. This ensures maximum product performance. (See the Stonchem Epoxy Primer Product Data Sheet for details.)

Note: Stonchem Epoxy Primer must be tack-free prior to application of the broadcast liquids.

APPLYING

Broadcast Liquids/Fiberglass Scrim Cloth/Broadcast

Individually stir amine and resin component to a smooth, uniform consistency and color. Any sediment in the container must be thoroughly scraped up and re-dispersed. Pour the entire contents of the resin and amine into a clean 20 liter mixing container. Mix in the mixing container using a heavy-duty, slow-speed drill(400 to 600 rpm) with a Jiffy Mixer for 2 minutes.

With a flat rubber squeegee and roller, apply a thin layer of broadcast liquids and set the fiberglass scrim cloth into the wet broadcast liquids. Overlap seams a minimum of 5 cm and apply a liberal amount of material between the overlapping layers. Use a flat trowel to smooth, flatten and embed the engineering fabric.

Once the engineering fabric is placed, using a steel squeegee and roller, apply a layer of broadcast liquids making sure to completely saturate fiberglass scrim cloth. This may require multiple passes in the opposite direction to achieve. Use a fully saturated nap roller to evenly level broadcast liquids. It is critical that the fabric be completely saturated and none left exposed.

While broadcast liquid is still wet, immediately broadcast with silica aggregate. Do not allow the aggregate to be broadcast ahead of the applicator. Broadcast the aggregate until a dry layer is achieved. Allow the material to cure. Remove the excess aggregate.

For the second broadcast layer of aluminum oxide, apply another layer of broadcast liquids using a flat, rubber squeegee and a medium nap roller. Once rolled and leveled, broadcast the aluminum oxide to refusal. Once this layers cures, remove the excess aggregate and prepare to apply the final topcoat.

Topcoat

Using a flat rubber squeegee and nap roller, apply the topcoat material to seal the exposed aggregate. A minimum of 375 micron will be required to adequately cover the exposed aggregate. More may be needed to meet the finish texture and the 3.81 mm thickness required by the job specification. Allow the material to cure.

Vertical Surfaces

Consult your local Stonhard representative or Stonhard's Technical Service Department for a recommendation.

PRECAUTIONS

- Acetone is recommended for clean up of Stonchem 658HD amine or resin spills.
- Use these materials only in strict accordance with the manufacturer's recommended safety procedures. Dispose of waste materials in accordance with government regulations.
- **The use of NIOSH approved respirators using an organic vapor/acid gas cartridge is mandatory.**
- The selection of proper protective clothing and equipment will significantly reduce the risk of injury. Body covering apparel, safety goggles or safety glasses and impermeable gloves are required.
- In case of contact, flush area with water for 15 minutes and seek medical attention. Wash skin with soap and water.
- If material is ingested, immediately contact a physician. **DO NOT INDUCE VOMITING.**
- Use only with adequate ventilation. Inhalation of vapors may cause severe headaches, nausea and possibly unconsciousness.
- During prep-work of floor substrate or mixing of Stonhard product while adding aggregate, dust masks must be worn.

NOTES


- Safety Data Sheets for Stonchem 658HD are available online at www.stonhard.com under Products or upon request.
- Specific information regarding the chemical resistance of Stonchem 658HD is available in the Stonchem 600 Series Chemical Resistance Guide.

- A staff of technical service engineers is available to assist with product application or to answer questions related to Stonhard products.
- Requests for technical literature or service can be made through local sales representatives and offices, or corporate offices located worldwide.
- The appearance of all floor, wall and lining systems will change over time due to normal wear, abrasion, traffic and cleaning. Generally, high gloss coatings are subject to a reduction in gloss, while matte finish coatings can increase in gloss level under normal operating conditions.
- Surface texture of resinous flooring surfaces can change over time as a result of wear and surface contaminants. Surfaces should be cleaned regularly and deep cleaned periodically to ensure no contaminant buildup occurs. Surfaces should be periodically inspected to ensure they are performing as expected and may require traction-enhancing maintenance to ensure they continue to meet expectations for the particular area and conditions of use.

CE MARKING

The harmonized European Standard EN 1504-2 „Products and systems for the protection and repair of concrete structures – Definitions, requirements, quality control and evaluation of conformity – Part 2 : Surface protection systems for concrete” gives specifications for products and systems based on methods “hydrophobic impregnation”, “impregnation” and “coating” for the various principles presented under EN 1504-9.

Products which fall under this specification have to be CE-labelled as per Annex ZA. 1, Tables ZA1a to ZA 1g according to the scope and relevant clauses there indicated and fulfill the requirements of the given mandate of the Construction Products Regulation nr. 305/2011.


Stoncor Europe Rue du Travail 9 1400 Nivelles, Belgium 22
DOP.658HD.2022.03.10 EN 1504-2
Surface Protection Product Ingress Protection 1.3(C) Physical Resistance 5.1(C)
Cap. Absorption & Permeability to Water Vapor.....W<0.1 kg/m ² *h ^{0.5} Water PermeabilityClass III Permeability to CO ₂S _d >50m Adhesion Strength by Pull-Off Test>2.0 MPa Fire ResistanceB _{fi} -s1 Abrasion Resistance.....<3000mg Impact ResistanceClass III

IMPORTANT:
 Stonhard believes the information contained here to be true and accurate as of the date of publication. Stonhard makes no warranty, expressed or implied, based on this literature and assumes no responsibility for consequential or incidental damages in the use of the systems described, including any warranty of merchantability or fitness. Information contained here is for evaluation only. We further reserve the right to modify and change products or literature at any time and without prior notice.

Rev.09/22
 © 2022 Stonhard www.stonhard.com



European Offices:

Belgium	+32 674 93 710	Spain	+34 933 623 785	Germany	+49 240 541 740
France	+33 160 064 419	Portugal	+351 227 535 642	The Netherlands	+31 165 585 200
Poland	+48 422 112 768	United Kindom	+44 1925 649 458	Italy	+39 022 53 751
		East Europe	+48 422 112 768		